COATING THICKNESS METER WITH EXTERNAL PROBE

OPERATING PRINCIPLE

Operating Principle	Application	For Example
(F Type) Magnetic induction	Can Measure the Thickness of non-magnetic coating layers on magnetic substrate	Such as :(aluminum, chrome, copper, enamel, rubber, paint) on magnetic substrate (steel, iron, alloy and magnetic stainless steel)
(NF Type) Eddy current	Can Measure the Thickness of nonconductive coating layers covered on nonferrous substrate	Such as: (Enamel, Rubber, Paint Vanish, Plastic anodic-oxide layer) covered on nonferrous substrate (Aluminum, Brass, Zinc, Tin and nonmagnetic stainless steel)



SPECIFICATION

MODEL:CM-8826FN

Measuring Range	0~1250um/0~50mil (Default Range)	
Resolution	0.1 / 1	
Accuracy	±1~3%n or ±2.5um	
Min. Radius Workpiece	F: Convex 1.5mm / Concave 25mm	
	N: Convex 3mm / Concave 50mm	
Min. Measuring Area	6mm	
Min. Sample Thickness	0.3mm	
Metric / Imperial	Convertible	
Power Supply	4x1.5V AAA Battery	
Low Battery Indication	Yes	
Dimension	126x65x27xmm	
Weight (Not including Battery)	81g	
	Main Unit	
	F Type probe	
Ctondord	N Type probe	
Standard Package List	F Calibration Base set	
T dokage List	N Calibration Base set	
	Calibration Foil set	
	Carrying Case	
	Instruction Manual	
Optional Accessories	Cable & Software for RS - 232C	

